


# MERCURY METALS



BRIGHT WHITE



CAMBRIDGE WHITE



WHITE-WHITE



BONE WHITE



SURF WHITE




REGENT GREY



STONE GREY



CHARCOAL



METRO BROWN



COFFEE BROWN



DARK BROWN



BLACK



TAN



BRIARWOOD TAN



ANTIQUE LINEN



GOLD



SAPPHIRE BLUE



SLATE BLUE



HERON BLUE



LABRADOR BLUE



ROYAL BLUE



BRIGHT RED



DARK RED



TILE RED



MELCHERS GREEN



FOREST GREEN



SPRUCE GREEN



SAGE GREEN



MIST GREEN



DEEP WATER GREEN



CABEC GREEN



TURQUOISE



PACIFIC TURQUOISE



COPPER PENNY



SILVER METALLIC

NOTE: COLOURS ON THIS CARD ARE REPRODUCED AS ACCURATLY AS MODERN PRINTING TECHNOLOGY WILL PERMIT.  
FREE MATERIAL SAMPLES ARE AVAILABLE UPON REQUEST.

# MERCURY METALS

COLOUR	QC NO. EQUIVALENT	22 GA	24 GA	26 GA	30 GA
METRO BROWN	228	•	•	•	•
DARK BROWN	229		•	•	
DARK RED	250	•	•	•	•
MIST GREEN	256	•	•	•	•
PACIFIC TURQUOISE	258		•	•	
TILE RED	259		•	•	•
SLATE BLUE	260	•	•	•	•
SAPPHIRE BLUE	261	•	•	•	•
BLACK	262		•	•	•
BONE WHITE	273	•	•	•	•
GOLD	276	•		•	
STONE GREY	305	•	•	•	•
CHARCOAL	306		•	•	•
MELCHERS GREEN	307	•	•	•	•
TURQUOISE	310	•		•	•
TAN	315	•	•	•	•
SURF WHITE	316	•	•	•	•
WHITE-WHITE	317	•	•	•	•
FOREST GREEN	329		•	•	
HERON BLUE	330	•	•	•	
BRAIRWOOD TAN	331		•	•	
BRIGHT RED	386	•	•	•	
ROYAL BLUE	790		•	•	•
REGENT GREY	1730	•	•	•	•
CABEC GREEN	2166		•		
DEEP WATER GREEN	3684		•	•	
LABRADOR BLUE	3688		•		
CAMBRIDGE WHITE	3695	•	•	•	
ANTIQUE LINEN	3696	•	•	•	
SPRUCE GREEN	3697		•		
SAGE GREEN	6089		•	•	
BRIGHT WHITE	4783				•
COFFEE BROWN	326			•	•

Standard Widths: 48" & 36" (also available in roll former widths and grades) Call for availability and costing.

## PERFORMANCE CHARACTERISTICS

Premium Silicon Modified Polyester Coil Coating

SPECIFICATION	TEST		RESULT
ASTM D-523	60 specular gloss	10-80	Gardner 60 meter or equivalent
NCCA II-12	Pencil Hardness	H – H2	No break in the film
NCCA II-10	Post Forming 180	1-T to 2-T	No pick off with Scotch #610 tape
ASTM D-2794	Reverse Impact, 60 inch pounds	Passes	No pick off with Scotch #610 tape
ASTM G-53	Q.U.V. Weatherometer, 1000 hrs	Passes	No objectionable chalking per ASTM D-659, Colour change per ASTM D-2244 or blistering per ASTM D-714.
ASTM D-2247	Humidity, 1000 hours at 100 F And 100% Humidity	Passes	Less than No. 8 blisters
ASTM B-117	Salt Spray 1000 hours 5% salt solution	Passes	Less than 5% No.6 blisters and less than 1/8" creep or tape off from the scribe per ASTM D-1654
ASTM D-2244-89	45 So. Florida Exposure 20 years colour retention	Passes	No objectionable colour change
ASTM D-659-86	45 So. Florida Exposure 20 years colour retention	Passes	No objectionable gloss loss or chalking
EMMAQUA	Accelerated Weathering 2,000,000 Langleys, Sun 10 Arizona exposure	Passes	No objectionable gloss loss, chalking, Colour change or blistering.